

In re Application of: Kodama et al.

Application No. 09/502,834

Filed: February 11, 2006

For: POLYBENZAZOLE ADHESIVE AND PRODUCTION METHOD THEREOF

COMMISSIONER OF PATENTS AND TRADEMARKS
Washington, D.C. 20231

Sir:

Transmitted herewith is a Response to Office Action in the subject application.

☐ Applicant claims small entity status of this application under 37 C.F.R. § 1.27

☒ **Petition For Extension Of Time**
☐ Applicant(s) petitions for a extension of time under 37 C.F.R. § 1.136, the fee for which is \$0.00 (enclosed).

☒ Applicant(s) believes that no petition for an extension of time is necessary. However, to the extent that such petition is deemed necessary, applicant(s) hereby petition for a sufficient extension of time to render the present submission timely. Please charge Deposit Account No. 12-1216 for the appropriate petition fee.

☒ No additional claim fee is required.

☒ Other: Partial English Translation of Priority Document (JP 036314/1999).

The claim fee has been calculated as shown below:

| | | | | | SMALL ENTITY | | OTHER THAN A SMALL ENTITY | |
|----------------------------------|--------------------------------------|-------|------------------------------------|----------------------|--------------|------------------|---------------------------|------------------|
| CLAIMS REMAINING AFTER AMENDMENT | | | HIGHEST NUMBER PREVIOUSLY PAID FOR | EXTRA CLAIMS PRESENT | RATE | ADDIT. CLAIM FEE | RATE | ADDIT. CLAIM FEE |
| TOTAL | 4 | MINUS | 20 | =0 | x 9= | \$0.00 | x 18= | \$0.00 |
| INDEPENDENT | 1 | MINUS | 3 | =0 | x 40= | \$0.00 | x 80= | \$0.00 |
| <input type="checkbox"/> | FIRST PRESENTATION OF MULTIPLE CLAIM | | | | + 130= | \$0.00 | + 260= | \$0.00 |
| | | | | | TOTAL | \$0.00 | TOTAL | \$0.00 |

☐ Please charge my Deposit Account No. 12-1216 in the amount of \$ 0.00. A duplicate copy of this sheet is attached.

☐ A check in the amount of \$0.00 is attached.

☒ The Commissioner is hereby authorized to charge payment of the following fees associated with this communication or credit any overpayment to Deposit Account No. 12-1216. A duplicate copy of this sheet is attached.

☒ Any filing fees under 37 C.F.R. § 1.16 for the presentation of extra claims.

☒ Any patent application processing fees under 37 C.F.R. § 1.17.

Respectfully submitted,

LEYDIG, VOIT & MAYER, LTD.

Leydig, Voit & Mayer, Ltd.
Two Prudential Plaza, Suite 4900
180 North Stetson
Chicago, Illinois 60601-6780
(312) 616-5600 (telephone)
(312) 616-5700 (facsimile)

By

John Kilyk, Jr.
John Kilyk, Jr., Reg. No. 30763
One of the Attorneys for Applicant(s)

RECEIVED
DEC 12 2002
TC 1700





PATENT
Attorney Docket No. 203924

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

Kodama et al.

Application No. 09/502,834

Filed: February 11, 2000

For: POLYBENZAZOLE ARTICLE AND
PRODUCTION METHOD THEREOF

Art Unit: 1711

Examiner: D. Truong

#12/C
12-1402

RECEIVED
DEC 12 2002
TC 1700

RESPONSE TO OFFICE ACTION

Commissioner for Patents
Washington, D.C. 20231

Dear Sir:

In response to the Office Action dated September 6, 2002, please enter the following amendments and consider the following remarks.

AMENDMENTS

IN THE SPECIFICATION:

Please replace the paragraph on page 11, lines 24-31, with the following:

C¹
A black solution was obtained by adding a small amount (less than about 1000 ppm) of a sodium hypochlorite solution to an aqueous solution of 2-aminophenol-4-sulfonamide (5% by weight) at 50°C, and the yarns prepared according to the method described in Example 1 were immersed therein for 60 seconds after neutralization step. The yarns were washed with water for 10 seconds and dried at 30°C for 120 seconds. The obtained fiber was folded 3 times and evaluated for resistance to light. The results are shown in Table 1.

IN THE CLAIMS:

Please amend claim 1 as follows:

C²
CWT
1. (Thrice Amended) A polybenzazole article superior in light resistance, which comprises a polybenzazole and a light-resisting agent that allows for a regular reflectance of the article of not more than 30% in not less than 30% of the wavelength region of from 450 nm to 700 nm, wherein the light-resisting agent is at least one member selected from the